

2 PACK EPOXY FLOOR PAINT

INTRODUCTION

To provide a hard wearing abrasion and chemical resistant floor coating.

AVAILABILITY

Supplied to customer requirements.
Numerous British Standard and special shades are available from stock.

PACKAGE SIZES

Supplied in 4 litres when mixed.

COMPOSITION

Based on an epoxy/polyamide resin system pigmented with suitable opacifying pigments dispersed in a high flash aromatic solvent.

APPEARANCE WHEN DRY

Gloss

SHELF LIFE

12 months minimum

SOLIDS BY WEIGHT

64% Typical

SOLIDS BY VOLUME

50 ± 2% Typical

SPECIFIC GRAVITY

1.15-1.25 kg/ltr

FLASH POINT

21°C - 55°C.

DRYING TIMES

Surface dry: 45 minutes at 18°C - 21°C.
To handle: 12 hours at 18°C - 21°C.

VISCOSITY AS SUPPLIED

As mixed

SURFACE PREPARATION

Blast tracking or acid etching is essential for optimum performance. **DO NOT** apply over single pack products.

THEORETICAL COVERAGE

Applied at 10²m per litre will give a DFT of 50µ.

APPLICATION

Brush, roller or airless spray. For airless spray use a 13-16 thou. tip size with a minimum tip pressure of 1800 p.s.i.

OVERCOATING

Coat on coat. Minimum 16 hours at 18°C - 21°C. Not more than 5 days.

SOLVENT FOR THINNING AND CLEANING EQUIPMENT

800/010 Thinners

HEALTH & SAFETY INFORMATION

This data should be read in conjunction with product safety data sheet 111.

ADDITIONAL INFORMATION

The details and information contained herein, are to the best of our knowledge correct but may from time to time be subject to revision. We will endeavour to keep customers informed of any changes that may occur but we advise that if in any doubt, contact is made with the manufacturer to establish the data is of the latest available. We would point out that whilst we have striven to ensure the details are as accurate as possible, we offer no guarantee as application conditions and techniques are beyond our control.