

## 2 PACK SOLVENT FREE EPOXY FLOOR COATING

### INTRODUCTION

A 2 pack solvent free self levelling epoxy coating. Ideally suited for application onto floor areas which are subject to chemical attack or heavy traffic use.

### AVAILABILITY

Supplied to customer requirements.  
Numerous British Standard and special shades are available from stock.

### PACKAGE SIZES

Supplied in 4 litres when mixed.

### COMPOSITION

Special blend of epoxy resin, pigments and polyamines.

### APPEARANCE WHEN DRY

Gloss

### SHELF LIFE

12 months minimum

### SOLIDS BY WEIGHT

100% Typical

### SOLIDS BY VOLUME

100% Typical

### SPECIFIC GRAVITY

1.1 - 1.2 Kg/Ltr

### FLASH POINT

Not applicable

### DRYING TIMES

Surface dry: 4 hours at 18°C - 21°C.  
Hard dry: 16 hours at 18°C - 21°C.

### VISCOSITY AS SUPPLIED

As mixed.

### SURFACE PREPARATION

Apply to blast tracked or acid etches surfaces which have been treated with epoxy sealer Ref.262/001.

### THEORETICAL COVERAGE

Applied at 8<sup>2</sup>m per litre will give a DFT of 125 $\mu$ .  
Applied at 2<sup>2</sup>m per litre will give a DFT of 500 $\mu$ .

### APPLICATION

Brush or roller.

### OVERCOATING

2 Pack Epoxy Coatings. Not less than 16 hours, not more than 72 hours at 18°C - 21°C.

### SOLVENT FOR THINNING AND CLEANING EQUIPMENT

Not applicable.

### HEALTH & SAFETY INFORMATION

This data should be read in conjunction with product safety data sheet CCL260.

### ADDITIONAL INFORMATION

The details and information contained herein, are to the best of our knowledge correct but may from time to time be subject to revision. We will endeavour to keep customers informed of any changes that may occur but we advise that if in any doubt, contact is made with the manufacturer to establish the data is of the latest available. We would point out that whilst we have striven to ensure the details are as accurate as possible, we offer no guarantee as application conditions and techniques are beyond our control.